

# FAST-TRACK 500

## FAST TRACK EMULSION

<b>Product Name</b>	<b>FAST-TRACK 500</b>
<b>Product Description</b>	Mr. Paint Man Fast-Track 500 is a self-priming water-based acrylic emulsion paint specially formulated with an excellent breathable property to promote rapid release of moisture from newly plastered walls.
<b>Designed Use</b>	Designed for use on interior and exterior masonry surface such as brickwork, plaster, cement panels and boards. It is suitable for use on both new and previously painted surfaces.
<b>Performance</b>	<ul style="list-style-type: none"> <li>• 5 Years warranty</li> <li>• Fast dry</li> <li>• Self-priming</li> <li>• Breathable paint film</li> <li>• Allow rapid moisture release</li> </ul>
<b>Performance Guide</b> <i>Film Properties</i> <i>Water Resistance</i>  <i>Theoretical Coverage</i> <i>No. of Coat</i>	Product will tolerate the atmospheric humidity levels present in normal exterior environment and will withstand moderate washing. Not suitable for use on immersed surfaces.  Approximately 10 - 12m <sup>2</sup> /litre 2 or more for best result
<b>Composition (nominal)</b> <i>Pigment</i> <i>Binder</i> <i>Solvent</i> <i>Volume Solid</i>	Lightfast Non-Lead Pigments and Mineral Extenders. Modified Acrylic Binder Water. 39%
<b>Finishing</b> <i>Colours</i> <i>Finishing</i> <i>Pack Size</i>	Refer to Kansai Paint's colour card Matt finishing 4.5 & 15 litres
<b>Application</b> <i>Drying Times</i>  <i>Dilution</i> <i>Cleaning Up</i>	Surface dry in 20 mins ; Recoat 1 - 2 hours <i>*Depend on temperature and humidity</i> Clean household water. Clean household water.
<b>Dilution Ratio</b> <i>Brush or Roller</i> <i>Conventional Spray</i> <i>Airless Spray</i>	Ready for use. If dilution is required, add up to 5-10% clean water. Add up to 1 part of clean water to 10 parts of paint (10%). Ready for use.
<b>Spray Equipment Guide</b> <i>Conventional Spray</i> <i>Airless Spray</i>	Satisfactory through most equipment. A typical set up for airless spray application would be a minimum working pressure on paint of 140Kg/cm <sup>2</sup> (2000 lb/sq in) with a spray tip size 0.58mm (23 thou) and a spray tip angle of 65°.
<b>Surface Preparation</b>	New wall must be allowed to cure and the moisture content should not exceed 20%. Ensure surfaces are sound, clean and free from contaminants and be thoroughly sand down using a suitable abrasive paper. When repainting, surfaces that remain powdery after cleaning must be primed with 1 coat of Mr. Paint Man 'Powdery Wall Adhesion Promoter'.

**Recommended Paint System**
**New, unpainted surfaces :**

<b>1<sup>st</sup> &amp; 2<sup>nd</sup></b>	
Fast-Track 500	Recoat 1 - 2 hours

**Repainting :**

<b>1<sup>st</sup></b>		<b>2<sup>nd</sup> &amp; 3<sup>rd</sup></b>	
Powdery Wall Adhesion Promoter	Recoat 4 - 5 hours	Fast-Track 500	Recoat 1 - 2 hours

**Safety & Health Information**

- Ensure adequate lighting and ventilation during application and drying.
- This product does not contain added lead or mercury.
- When applying paints, it is advisable to wear eye protection.
- In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.
- Use soap and water to remove splashes from skin.
- Storage: Keep container closed and store in clean and dry conditions.
- Dispose of contents and container in accordance with all local, regional, national and international regulations.
- Do not empty into drains or water courses.
- This product is not flammable. Keep out of reach of children.
- Safety Data Sheet (SDS) is available upon request.

For further information on Product Data, please contact :

**Decorative Sales Department**

Kansai Paint Asia Pacific Sdn. Bhd. (705919-w)

9-3A, 9-5, 9-6 & 9-7, Level 9, Port Tech Tower, Jalan Tiara 3/KU1, Bandar Baru Klang, Selangor Darul Ehsan, Malaysia.

Website : [www.kansaimalaysia.com](http://www.kansaimalaysia.com) Tel : +603 3002 4001 Fax : +603 3002 4002

*\*Practical coverage will vary according to the roughness and porosity of surface to be painted, the application method and condition, dry film and thickness and the skill of applicator.*

*The information in this technical data sheet is given to the best of our knowledge based on laboratory testing and practical experience and is provided as a general advice only. No guarantee of results is implied since the conditions of use are beyond our control. It is the responsibility of the users to ensure the suitability and proper usage of the product. We reserve the right to change the data without prior notice.*