

PEARL MATT

MATT FINISH FOR INTERIOR WALLS

Product Name	PEARL MATT
Product Description	Mr. Paint Man Pearl Matt is an elegant matt pearl finish for interior.
Designed Use	For use on new or previously painted interior masonry surfaces such as brickwork, plaster and cement rendering.
Performance	<ul style="list-style-type: none"> • 5.5 Years warranty • Excellent coverage • Good hiding power • Easy clean • Washable properties • Easy to use • No added lead or mercury • Low VOC and odour
Performance Guide <i>Film Properties</i> <i>Water Resistance</i> <i>Theoretical Coverage</i> <i>No. of Coat</i>	Product will tolerate the atmospheric humidity levels present in normal interior environment and will withstand moderate washing. Approximately 10 - 12m ² /litre 2 or more for best result
Composition (nominal) <i>Pigment</i> <i>Binder</i> <i>Solvent</i> <i>Volume Solid</i>	Lightfast Non-Lead Pigments and Mineral Extenders. PVA Copolymer Emulsion Water 35%
Finishing <i>Colours</i> <i>Finishing</i> <i>Pack Size</i>	Refer to Kansai Paint's colour card Matt finishing 0.9 & 4.5 litres
Application <i>Drying Times</i> <i>Dilution</i> <i>Cleaning Up</i>	Surface dry in 20 mins ; Recoat 1 - 2 hours <i>*Depend on temperature and humidity</i> Clean household water. Clean household water.
Dilution Ratio <i>Brush or Roller</i> <i>Conventional Spray</i> <i>Airless Spray</i>	For sealing new or bare surfaces thin with up to 1 part of clean water to 5 parts of paint (20%). For normal use, thinning is usually not necessary. If required, should not exceed 1 part of clean water to 10 parts of paint (10%). Add up to 1 part of clean water to 5 parts of paint (20%). Ready for use.
Spray Equipment Guide <i>Conventional Spray</i> <i>Airless Spray</i>	Satisfactory through most equipment. A typical set up for airless spray application would be a minimum working pressure on paint of 140kg/cm ² (2000 lb/sq in) with a spray tip size 0.58mm (23 thou) and a spray tip angle of 65°
Surface Preparation and System Information	Repair all minor defects with suitable fillers. Ensure surfaces are dry, clean and free from contaminants. For new walls, apply 1 coat of Mr. Paint Man 'New Wall Alkali Resistant Primer Sealer'. When repainting, for surfaces that remain powdery after cleaning, apply 1 coat of Mr. Paint Man 'Powdery Wall Adhesion Promoter'.

Recommended Paint System
New, unpainted surfaces :

1 st		2 nd & 3 rd	
New Wall Alkali Resistant Primer Sealer	Recoat 1 - 2 hours	Pearl Matt	Recoat 1 - 2 hours

Repainting :

1 st		2 nd & 3 rd	
Powdery Wall Adhesion Promoter	Recoat 4 - 5 hours	Pearl Matt	Recoat 1 - 2 hours

Safety & Health Information

- Ensure adequate lighting and ventilation during application and drying.
- This product does not contain added lead or mercury.
- When applying paints, it is advisable to wear eye protection.
- In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.
- Use soap and water to remove splashes from skin.
- Storage: Keep container closed and store in clean and dry conditions.
- Dispose of contents and container in accordance with all local, regional, national and international regulations.
- Do not empty into drains or water courses.
- This product is not flammable. Keep out of reach of children.
- Safety Data Sheet (SDS) is available upon request.

For further information on Product Data, please contact :

Decorative Sales Department

Kansai Paint Asia Pacific Sdn. Bhd. (705919-w)

9-3A, 9-5, 9-6 & 9-7, Level 9, Port Tech Tower, Jalan Tiara 3/KU1, Bandar Baru Klang, Selangor Darul Ehsan, Malaysia.

Website : www.kansaimalaysia.com Tel : +603 3002 4001 Fax : +603 3002 4002

**Practical coverage will vary according to the roughness and porosity of surface to be painted, the application method and condition, dry film and thickness and the skill of applicator.*

The information in this technical data sheet is given to the best of our knowledge based on laboratory testing and practical experience and is provided as a general advice only. No guarantee of results is implied since the conditions of use are beyond our control. It is the responsibility of the users to ensure the suitability and proper usage of the product. We reserve the right to change the data without prior notice.