

PAR SUPERGLOSS

BRILLIANT GLOSS ENAMEL FOR WOOD & METAL

Product Name	PAR SUPERGLOSS
Product Description	PAR Supergloss is a premium grade, high performance enamel suitable for use on all types of wood and metal. PAR Supergloss gives a tough, mirror-like high gloss finish and has excellent weathering and fungus resistance.
Designed Use	For use on new or previously painted, interior and exterior wood (door, windows, fascia boards, etc), metal (m.s. gates, grilles) and properly primed masonry surfaces such as brickwork, plaster, cement rendering and asbestos cement where a high gloss finish is desired.
Binder Type	Oil modified alkyd enamel
Performance	<ul style="list-style-type: none"> • Brilliant gloss enamel • Outstanding weathering resistance • Excellent fungus resistance • Excellent hiding power • Excellent colour retention • No added lead or mercury • Approved by SIRIM to Malaysian Standard MS 125:1995
Physical Properties Coverage* Volume Solids Dry Film Thickness Wet Film Thickness Flash Point	12 – 15 m ² /Lt @ 30 microns 45% 30 microns / coat 67 microns / coat 32°C
Finishing Colours Finishing Pack Size	Refer to Kansai Paint's colour card Mirror-like high gloss 1 & 5 litres
Application Drying Times Dilution Cleaning Up	Surface dry : 2 – 3 hours; Recoat : 8 hours (Overnight for the best results) <i>*Depend on temperature and humidity</i> White Spirit White Spirit
Dilution Ratio Brush or Roller Conventional Spray Airless Spray	Ready for use. If dilution is required, add up to 5% white spirit. Dilution up to 10% white spirit. Ready for use.
Spray Equipment Guide Conventional Spray Airless Spray	A typical set up would be a minimum atomising pressure of 2.8 kg/cm ² and fluid pressure of 0.4 kg/cm ³ with a nozzle size of 1.27 mm. A typical set up would be a minimum of 155 kg/cm ³ with nozzle size of 0.38 - 0.43 mm and a spray tip angle of 65°.
Surface Preparation	Metal Using mineral turpentine, remove all grease, wax and surface contaminants. Lightly abrade surfaces and dust off. Previously painted surfaces must be thoroughly rubbed down using a suitable abrasive paper. Remove all grease, wax and surface contaminants by solvent wiping with mineral turpentine.

	<p>Wood Surfaces must be clean, dry and free from all defective or poorly adhering materials. For highly resinous wood, apply a coat of PAR Aluminium Wood Primer to seal the surfaces. Previously painted surfaces must be thoroughly rubbed down using a suitable abrasive paper. Remove all grease, wax and surface contaminants by solvent wiping with mineral turpentine.</p>								
Recommended Paint System	<p>New, unpainted surfaces: Metal</p> <table border="1"> <thead> <tr> <th>1st</th> <th>Recoat</th> <th>2nd & 3rd</th> <th>Recoat</th> </tr> </thead> <tbody> <tr> <td>PAR Red Oxide Primer or PAR Zinc Phosphate Primer</td> <td>6 hours</td> <td>PAR Supergloss</td> <td>8 hours</td> </tr> </tbody> </table>	1 st	Recoat	2 nd & 3 rd	Recoat	PAR Red Oxide Primer or PAR Zinc Phosphate Primer	6 hours	PAR Supergloss	8 hours
	1 st	Recoat	2 nd & 3 rd	Recoat					
	PAR Red Oxide Primer or PAR Zinc Phosphate Primer	6 hours	PAR Supergloss	8 hours					
	<p>New, unpainted surfaces : Galvanised Iron & Aluminium</p> <table border="1"> <thead> <tr> <th>1st</th> <th>Recoat</th> <th>2nd</th> <th>Recoat</th> </tr> </thead> <tbody> <tr> <td>PAR Wash Primer</td> <td>1 hour</td> <td>PAR Red Oxide Primer or PAR Zinc Phosphate Primer</td> <td>16 hours (Overnight)</td> </tr> </tbody> </table>	1 st	Recoat	2 nd	Recoat	PAR Wash Primer	1 hour	PAR Red Oxide Primer or PAR Zinc Phosphate Primer	16 hours (Overnight)
	1 st	Recoat	2 nd	Recoat					
PAR Wash Primer	1 hour	PAR Red Oxide Primer or PAR Zinc Phosphate Primer	16 hours (Overnight)						
<table border="1"> <thead> <tr> <th>3rd & 4th</th> <th>Recoat</th> </tr> </thead> <tbody> <tr> <td>PAR Supergloss</td> <td>8 hours</td> </tr> </tbody> </table>	3 rd & 4 th	Recoat	PAR Supergloss	8 hours					
3 rd & 4 th	Recoat								
PAR Supergloss	8 hours								
<p>New, unpainted surfaces : Wood</p> <table border="1"> <thead> <tr> <th>1st</th> <th>Recoat</th> <th>2nd</th> <th>Recoat</th> </tr> </thead> <tbody> <tr> <td>PAR Aluminium Wood Primer</td> <td>16 hours (Overnight)</td> <td>PAR Undercoat</td> <td>6 – 7 hours</td> </tr> </tbody> </table>	1 st	Recoat	2 nd	Recoat	PAR Aluminium Wood Primer	16 hours (Overnight)	PAR Undercoat	6 – 7 hours	
1 st	Recoat	2 nd	Recoat						
PAR Aluminium Wood Primer	16 hours (Overnight)	PAR Undercoat	6 – 7 hours						
<table border="1"> <thead> <tr> <th>3rd & 4th</th> <th>Recoat</th> </tr> </thead> <tbody> <tr> <td>PAR Supergloss</td> <td>8 hours</td> </tr> </tbody> </table>	3 rd & 4 th	Recoat	PAR Supergloss	8 hours					
3 rd & 4 th	Recoat								
PAR Supergloss	8 hours								
Safety & Health Information	<p>Repainting: Wood</p> <table border="1"> <thead> <tr> <th>1st</th> <th>Recoat</th> <th>2nd & 3rd</th> <th>Recoat</th> </tr> </thead> <tbody> <tr> <td>PAR Undercoat</td> <td>6 – 7 hours</td> <td>PAR Supergloss</td> <td>8 hours</td> </tr> </tbody> </table>	1 st	Recoat	2 nd & 3 rd	Recoat	PAR Undercoat	6 – 7 hours	PAR Supergloss	8 hours
	1 st	Recoat	2 nd & 3 rd	Recoat					
PAR Undercoat	6 – 7 hours	PAR Supergloss	8 hours						
<p><i>Limitations : Not suitable for use in severely aggressive exposure environment.</i></p> <ul style="list-style-type: none"> • Ensure adequate lighting and ventilation during application and drying. • This product does not contain added lead or mercury. • When applying paints, it is advisable to wear eye protection. • In case of contact with eyes, rinse immediately with plenty of water and seek medical advice. • Use soap and water to remove splashes from skin. • Storage: Keep container closed and store in clean and dry conditions. • Do not empty into drains or water courses. • This product is not flammable. Keep out of reach of children. • Safety Data Sheet (SDS) is available upon request. 									

For further information on Product Data, please contact :

Decorative Sales Department

Kansai Paint Asia Pacific Sdn. Bhd. (705919-w)

9-3A, 9-5, 9-6 & 9-7, Level 9, Port Tech Tower, Jalan Tiara 3/KU1, Bandar Baru Klang, Selangor Darul Ehsan, Malaysia.

Website : www.kansaimalaysia.com Tel : +603 3002 4001 Fax : +603 3002 4002

**Practical coverage will vary according to the roughness and porosity of surface to be painted, the application method and condition, dry film and thickness and the skill of applicator.*

The information in this technical data sheet is given to the best of our knowledge based on laboratory testing and practical experience and is provided as a general advice only. No guarantee of results is implied since the conditions of use are beyond our control. It is the responsibility of the users to ensure the suitability and proper usage of the product. We reserve the right to change the data without prior notice.